



DATA SHEET

Magnesiumoxid PENTOMAG 6200

Analytical Method / X-Ray Fluorescence DIN 51001

| | |
|-------------------------------|----------------------|
| Magnesiumoxide (MgO) | >92 % |
| CaO | <2,10 % |
| Fe2O3 | <0,65 % |
| SiO2 | <1,70 % |
| Al2O3 | <0,25 % |
| LOI (Loss on Ignition) | <3,00 % |
| Size | 95% passing 200 mesh |
| Packaging | Big bags of 1,000 kg |

Above data have been determined with utmost care and should be reliable. Nevertheless, any recommendations made are without guarantee, since conditions of use are beyond our control.

April 20, 2021

PENTOL-ENVIRO AG

CH-4002 Basel/Schweiz
Nauenstrasse 63a
www.pentol.net

Tel.: +41 (0)61 272 93 90
Fax: +41 (0)61 272 93 94
e-Mail: office.ch@pentol.net

MWST Nr. CHE-105.822.524
DE St-Nr. 09423/13852
USt-IdNr. DE813695352